


DESCRIPTION			
Total Thickness	EN ISO 24346	mm	2
Thickness of the wearlayer	EN ISO 24340	mm	0,30
Weight	EN ISO 23997	g/m <sup>2</sup>	3580
Size	EN ISO 24342	mm	457 x 914 mm / 11 / 4,60 m <sup>2</sup> 610 x 610 mm / 13 / 4,83 m <sup>2</sup> 184 x 1219 mm / 21 / 4,71 m <sup>2</sup> 230 x 1500 mm / 13 / 4,49 m <sup>2</sup> 184 x 1219 mm (EIR) / 17 / 3,81 m <sup>2</sup> 230 x 1500 mm (EIR) / 11 / 3,8 m <sup>2</sup>
Number of planks /tiles and sqm per box	-	pcs/m <sup>2</sup>	
CLASSIFICATION			
Norm/Product Specification	-	-	EN ISO 10582
European Classification	EN ISO 10874	class	23 - 31
Fire Rating	EN 13 501-1	class	Bfl-s1
Static Electrical Propensity	EN 1815	kV	< 2
Slip Resistance Wet	EN 16165 app. B (DIN 51130)	class	R10
PERFORMANCES			
Wear Resistance	EN 660.2	mm <sup>3</sup>	< 2,0
Wear Group	-	group	T
Type Binder content	ISO 10582	group	I
Room Impact	NF S 31074	dB	77
Impact sound insulation	EN ISO 717-2	dB	4
Dimensional stability (norm)	EN ISO 23999	%	≤ 0,25
Dimensional stability (average measured value)	-	%	≤ 0,10
Residual Indentation	EN ISO 24343-1	mm	≤ 0,10
Castor chair test	ISO 4918	-	OK
Thermal Conductivity	EN ISO 10456	W/(m.K)	0,25
Thermal Resistance	EN ISO 10456	m <sup>2</sup> .K/W	0,008
Colour Fastness	EN ISO 105-B02	degree	≥ 6
Surface Treatment	-	-	PUR+ Matt
Chemical Products Resistance	EN ISO 26987		OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10
CE MARKING			
	EN 14041		